0-37-200447-8

25 September 1967

Page 1 of 3

EVALUATION SUMMARY

Mission BX-6722

1. Processing and Titling - Performed in field

2. Physical Condition - Good

3. Hypo Retention - High; rewashing required

4. Exposure (based on density) - Medium to low

5. General Comments:

A. Cloud Cover = 50%.

- B. Mission could not be cleaned with the takky roller unit. Title pickoffs occurred. Parts were cleaned with a Clinton cleaner waxer.
- C. Minus density streaks were observed in light areas of several parts. (Example: Part 2)
- D. Kinks and dirt were on a few frames.
- E. Part 10 was severely damaged (creases, base and emulsion scratches) during the reproduction operation.

Page 2 of 3

MISSION NO. BX-6722 EVALUATION REPORT

Evaluated By Q.C. Technicia	ins Camera_	Fwd/Aft	
Evaluation Date 19 September	er 1967 Emulsion	3404	
-			
Film Metering	Erratic on some parts.	Example Part 7	
Film Tracking	Good		
Clock Operation Exposure	Good		
Counter	Good		
Data Chamber (image quality)	Good		
Apparent Resolution	Normal		
Apparent Granularity	Normal		
Density	Light to medium		
Contrast	Medium		

Discrepancies:

<u>Part</u>	Frames	<u>Comments</u>
1	H-T 1-9 1	Emulsion scratch Fog Crease
2	98 , 133 145	Emulsion scratch Pinholes
3	154,224 193	Emulsion scratch Pinholes
14	229 230 231,246	Emulsion scratch Crease Digs
5	328 - 329 379 - 380	Splice Stain
6		
7	474-492 530-531	Fog Splice
8	574 606 - 607 607	Crease

Crease
Approved For Release 2005/02/10 : CIA-RDP75B00159R000400040020-2

Page 3 of 3

Fwd/ <u>Discrepancies (Cont'd)</u> Aft Camera

Part	Frames	Comments)
9	686,688,754 734,738 753-755 755-758 757,760 759	Emulsion pickoff Emulsion dig Title flake off Wrinkled edge Splice Abrasions	
10	622 , 623 624 - 683 623 - 635 657 - 673	Creases Severe emulsion and base scratches Creases, emulsion scrape """ Transverse crease	
11	761 795,813 822,823 822	Crease Emulsion digs Splice Emulsion scratch	
12	843,870,874 844 H-T	Emulsion pickoff Emulsion dig Minus density streak	
13	913,935,937,956 914,944,951,983 961 985 H-T	Emulsion dig Emulsion pickoff Wrinkle edge Fog Minus density streak, intermittent band	ling
14	H - T	Minus density streak	